
TECH N

TECHON PFA

- Plenum Suitable
- FAR 25 Approved
- **Expands Up To 150%**
- Resists Gasoline And Other Chemicals
- Cut And Abrasion Resistant

				r de ops			
Nominal	Part #	Expansion Range		Bulk	Shop	Available	Lbs/
Size		Min	Max	Spool	Spool	Colors	100′
1/8"	TFN0.13NT	3/32"	1/4"	1,000′	225′	Natural	0.50
1/4"	TFN0.25NT	3/16"	3/8"	1,000′	200′	Natural	0.68
3/8"	TFN0.38NT	1/4"	3/4"	500′	125'	Natural	2.20
1/2"	TFN0.50NT	3/8"	7/8"	500′	100′	Natural	2.60
3/4"	TFN0.75NT	5/8"	1 1/4"	250′	75′	Natural	2.90
1 1/4"	TFN1.25NT	1 1/8"	1 1/2"	200′	50′	Natural	4.80
1 3/4"	TFN1.75NT	1 3/8"	1 3/4"	200′	50′	Natural	5.50
2"	TFN2.00NT	1 11/16"	2 1/8"	200′	25′	Natural	6.40
Overexpanded							
1/2"	TFO0.50NT	3/8"	1"	500′	100′	Natural	2.60

Put-Ups



High Temp Stable, Abrasion Resistant, Low Outgassing


TECHON PFA (TF) expandable sleeving is ideal in applications where flame, chemical and very high temperature resistance are significant considerations. Braided from 16 mil perfluoroalkoxy (PFA) polymer monofilament.

The high temperature properties of TF make it the ideal choice for aerospace, military and high-tech applications where thermal stability and low outgassing are critical. TF is suitable for plenum applications.

What Makes Techon PFA so Special?

Techon PFA is inert to virtually all chemicals and is considered the most slippery material on the planet. These properties have made it one of the most valuable and versatile technologies ever invented, contributing to advancements in areas such as aerospace, communications, electronics, industrial processes and architecture.

Colors Available:
Natural (NT)



Material

Perfluoroalkoxy

Grade

TFN

Monofilament Diameter

.016"

Drawing Number

TF001TF-WD



High temperature resistance and low outgassing allows Techon PFA sleeving to function in high-temp environments.



Technical Data Sheet

TECHON PFA





Abrasion Resistance Very High

Abrasion Test Machine Taber 5150

Abrasion Test Wheel Calibrase H-18

Abrasion Test Load 500g

Room Temperature 71°F

Humidity 59%

Slight Rough Surface And A Few Filaments Broken 1,500 Test Cycles

Visible Wear And Three Filaments Broken 2,000 Test Cycles

Material Destroyed 3,000 Test Cycles

Pre-Test Weight 13,955.5 mg

Post-Test Weight 12,911.9 mg


Test End Loss Of Mass Point Of Destruction 1,043.6 mg



Chemical Resistance 1=No Effect

4=More Affected 2=Little Effect 5=Severely Affected 3=Affected

Aromatic Solvents	1
Aliphatic Solvents	1
Chlorinated Solvents	1
Weak Bases	1
Salts	1
Strong Bases	1
Salt Water <i>0-S-1926</i>	
Hydraulic Fluid MIL-H-5606	
Lube Oil MIL-L-7808	1
De-Icing Fluid MIL-A-8243	
Strong Acids	1
Strong Oxidants	1
Esters/Keytones	2
UV Light	1
Petroleum	
Fungus ASTM G-21	
Halogen Free	
RoHS	
SVHC	



PHYSICAL PROPERTIES

Monofilament Diameter ASTM D-204	016						
Flammability RatingF	FAR 25						
Recommended CuttingHot Wire	/Knife						
Colors	1						
Wall Thickness	04						
Tensile Strength (Yarn)	2.1						
Specific Gravity ASTM D-792	_2.15						
Moisture Absorption % ASTM D-570	_<.01						
Hard Vacuum Data ASTM E-595 at 10-5 torr							
TML	00						
CVCM	00						
WVR	0						
Smoke D-Max ASTM E-662							
OutgassingVer	y Low						
Oxygen Index	_>95						

© 2012 Techflex, Inc. - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex, Inc. is strictly forbidden.